



SWASAN
GLOBALISED

SWAMILL & SHRIPLAS
ETHYLENE VINYL ACETATE

SWAMILL & SHRIPLAS ETHYLENE VINYL ACETATE	EVA 6001	EVA 6002	EVA 8001	EVA 8002	EVA 8003
Vinyl Acetate %	18	18	28	28	28
Melting Range °C	90 – 100	85 – 95	80 – 90	75 – 85	70 – 80
MFI g/10min	20	150	25	150	400
Density g/cm ³	0.950	0.950	0.953	0.956	0.956
Fusing Temp. °C	110 – 120	105 – 115	90 – 100	85 – 95	80 – 90
Laundry up to °C	50	40	40	40	40
Thermal Stability °C	70	60	65	55	55
Particle Size μ	0-250/0-300/0-400	0-250/0-300/0-400	0-250/0-300/0-400	0-300/0-400/0-500	0-300/0-400/0-500

- 0-300 / 0-400 / 0-500 for Scatter / Sugar Coatings
- 0-250 for Micro Dot Coatings
- Other specific Fineness available upon request

* Melt Index measured by 2.16kg / 190°C

The information and data contained herein are believed to be correct. However, we do not warrant either expressly or by implication, the accuracy thereof. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale. No statement in this bulletin is to be construed as violating any copyright or patent.